



Specifications of Coal Tar Pitch (PA61X/L)

No.	Test Type	Method	Method	Unit	Limit
1	Softening Point (Mettler)	ASTM D3104	WI-50-01	°C	110 - 120
2	QI	STPTC PT11-79	WI-50-01	%	Min. 3
3	TI	STPTC PT7-79	WI-50-01	%	Min. 25
4	Ash Content	ASTM D2415	WI-50-01	%	Max. 0.3
5	Coking Value	ISO 6998	WI-50-01	%	Min. 50
6	Density	ASTM D4892	WI-50-01	gr/cm ³	1.27-1.4
7	Beta Resin	STPTC PT7-79	WI-50-01	-	20-30
8	Moisture	ASTM D95	WI-50-01	%	Max. 0.2
9	Sodium	Flame photometer method	WI-50-01	ppm	Max. 200
10	Distillation (0-360°C)	ASTM D2569	WI-50-01	%	3-15

امكان تحويل به صورت مایع و جامد می باشد.