



Specifications of Coal Tar Pitch (PA81X/L)

No.	Test Type	Method	Unit	Limit		
1	Softening Point (Mettler)	ASTM D3104	WI-50-01	°C	98-102	
2	QI	STPTC PT11-79	WI-50-01	%	6-11.5	
3	TI	STPTC PT7-79	WI-50-01	%	Min. 28	
4	Ash Content	ASTM D2415	WI-50-01	%	Max. 0.3	
5	Coking Value	ISO 6998	WI-50-01	%	Min. 41	
6	Density	ASTM D4892	WI-50-01	gr/cm ³	1.27-1.30	
7	Beta Resin	STPTC PT7-79	WI-50-01	-	Min. 22	
8	Moisture	ASTM D95	WI-50-01	%	Max. 0.5	
9	Distillation (0-360°C)	0-270°C 270-360°C	ASTM D2569	WI-50-01	%	Max 1 Max 4

امكان تحويل بصورت مایع و جامد می باشد.