



## Specifications of Low Softening Point Pitch (PL01X)

No.	Test Type	Method	Unit	Limit	
1	Softening Point (Mettler)	ASTM D3104	WI-50-01	°C	55-60
2	QI	STPTC PT11-79	WI-50-01	%	4-8
3	TI	STPTC PT7-79	WI-50-01	%	20-30
4	Ash Content	ASTM D2415	WI-50-01	%	Max. 0.2
5	Coking Value	ISO 6998	WI-50-01	%	40-45
6	Beta Resin	STPTC PT7-79	WI-50-01	-	Min. 15
7	Density	ASTM D4892	WI-50-01	gr/cm <sup>3</sup>	1.2-1.3